

Dyneema® HMPTE

Promjer / dia. mm	Opseg inch	Težina kg/100 m	MBL t	MBL kN
6	3/4	2,3	4,2	41,2
8	1	3,9	6,7	65,7
10	1-1/4	5,9	10,8	105,9
12	1-1/2	9,5	16,5	161,9
14	1-3/4	12,8	22,0	215,8
16	2	16,0	27,5	269,8
18	2-1/4	20,8	35,0	343,3
20	2-1/2	25,5	41,5	407,1
22	2-3/4	30,5	50,0	490,5
24	3	35,8	58,0	569,0
26	3-1/4	41,0	66,0	647,4
28	3-1/2	46,5	74,0	725,9
30	3-3/4	52,0	81,5	799,5
32	4	57,0	88,5	868,2
34	4-1/4	62,5	96,0	941,7
36	4-1/2	68,0	104,0	1020,2
38	4-3/4	74,0	112,0	1098,7
40	5	84,0	127,0	1245,8
42	5-1/4	93,0	140,0	1373,4
44	5-1/2	102,0	152,0	1491,1
46	5-3/4	110,0	165,0	1618,6
48	6	121,0	179,0	1755,9
50	6-1/4	131,0	193,0	1893,3
52	6-1/2	141,0	206,0	2020,8
56	7	163,0	236,0	2315,1
60	7-1/2	175,0	252,0	2472,0
64	8	200,0	282,0	2766,3
68	8-1/2	226,0	316,0	3099,9
72	9	254,0	348,0	3413,8
80	10	313,0	422,0	4139,7
88	11	379,0	503,0	4934,3
96	12	451,0	588,0	5768,1
104	13	531,0	641,0	6284,3
112	14	615,0	736,0	7215,6
120	15	710,0	836,0	8196,0
128	16	805,0	940,0	9215,6